






HY2149-09


BY HOAU BROTHER




HY2149-09




HY2149-22




HY2149-21




HY2149-20




HY2149-18




HY2149-19




HY2149-17




HY2149-16




HY2149-15




HY2149-14




HY2149-13




HY2149-10




HY2149-11




HY2149-12




HY2149-23




HY2149-07



HY2149-06




HY2149-01




HY2149-08




HY2149-04



HY2149-02



HY2149-03



HY2149-05



技术检测 (Tec.)	检测标准 (TS.)	项目 (Unit.)		测试结果 (Test Result)	
耐水色牢度 (CFTW.)	AATCC107:2002 GB/T5713-1997	污染-Srain	褪色-Fading	Grade	4
		污染-Srain	褪色-Fading	等级	4
耐汗色牢度 (CFTP.)	AATCC15:2002 GB/T3922-1997	污染-Srain	褪色-Fading	Grade	4
		污染-Srain	褪色-Fading	等级	4
耐洗色牢度 (CFTW.)	ISO 105-C03:1989 GB/T3921.3-1997	污染-Srain	褪色-Fading	Grade	4
		污染-Srain	褪色-Fading	等级	4
干湿摩擦色牢度 (CFTR.)	AATCC8:2002 GB/T3920-1997	干-Dry	湿-Wet	Grade	4
		干-Dry	湿-Wet	等级	4
抗摩擦坚牢度 (Ab.Re)	ASTM D4966-98 Martindale 12Kpa			rubs	50000转

colour 23

材质(Comp):100%涤纶(PL)
克重(Weight):320gsm
幅宽(Width):150cm

备注:我司面料未含阻燃,阻燃需外加工.



Company Information

Contact		
☎ (Phone)	0757-23870666	23636258
☎ (Fax)	0757-23875234	23873536
✉ (E-mail)	xiaowensu@hoaubrother.com	
🌐 (Web)	www.hoaubrother.com	
📍 (Add)	顺德·龙江	精美路18号世博汇A座4楼(华宇总部) 亚洲国际A区一排29-32号(华宇旗舰店) No. 29-32, A area, Asia international materials city, Long Jiang, Shunde, Foshan, Guangdong, China, Post Code 528318



扫描二维码, 关注华宇兄弟

• 产品数据为真实检测数据 •