




HY2170-24

BY HOAU BROTHER



HY2170-24




HY2170-01



HY2170-02




HY2170-03




HY2170-21




HY2170-05



HY2170-06



HY2170-07



HY2170-08



HY2170-09



HY2170-10



HY2170-11



HY2170-12



HY2170-14



HY2170-13



HY2170-15



HY2170-16



HY2170-17



HY2170-18



HY2170-19



HY2170-20



HY2170-22



HY2170-23



HY2170-25



HY2170-26



HY2170-27




HY2170-04



HY2170-29



HY2170-28



HY2170-30



HY2170-31



HY2170-32

技术检测 (Tec.)	检测标准 (TS.)	项目 (Unit.)		测试结果 (Test Result)	
耐水色牢度 (CFTW.)	AATCC107:2002 GB/T5713-1997	污染-Srain	褪色-Fading	Grade	4
		污染-Srain	褪色-Fading	等级	4
耐汗色牢度 (CFTP.)	AATCC15:2002 GB/T3922-1997	污染-Srain	褪色-Fading	Grade	4
		污染-Srain	褪色-Fading	等级	4
耐洗色牢度 (CFTW.)	ISO 105-C03:1989 GB/T3921.3-1997	污染-Srain	褪色-Fading	Grade	4
		污染-Srain	褪色-Fading	等级	4
干湿摩擦色牢度 (CFTR.)	AATCC8:2002 GB/T3920-1997	干-Dry	湿-Wet	Grade	4
		干-Dry	湿-Wet	等级	4
抗摩擦坚牢度 (Ab.Re)	ASTM D4966-98 Martindale 12Kpa			rubs	50000转

colour 32

材质(Comp):100%涤纶(PL)

克重(Weight):300gsm

幅宽(Width):145cm

备注:我司面料未含阻燃,阻燃需外加工.



Company Information

Contact		
	(Phone)	0757-23870666 23636258
	(Fax)	0757-23875234 23873536
	(E-mail)	xiaowensu@hoaubrother.com
	(Web)	www.hoaubrother.com
	(Add)	顺德•龙江 精美路18号世博汇A座4楼(华宇总部) 亚洲国际A区一排29-32号(华宇旗舰店) No. 29-32,A area, Asia international materials city,Long Jiang, Shunde,Foshan, Guangdong, China,Post Code 528318



扫描二维码, 关注华宇兄弟

• 产品数据为真实检测数据 •