



HY2187-07


BY HOAU BROTHER




HY2187-01




HY2187-07




HY2187-06




HY2187-03




HY2187-05




HY2187-02




HY2187-04




HY2187-11




HY2187-12



HY2187-08



HY2187-09



HY2187-10

技术检测 (Tec.)	检测标准 (TS.)	项目 (Unit.)	测试结果 (Test Result)
耐水色牢度 (CFTW.)	AATCC107:2002	污染-Srain 褪色-Fading	Grade 4
	GB/T5713-1997	污染-Srain 褪色-Fading	等级 4
耐汗色牢度 (CFTP.)	AATCC15:2002	污染-Srain 褪色-Fading	Grade 4
	GB/T3922-1997	污染-Srain 褪色-Fading	等级 4
耐洗色牢度 (CFTW.)	ISO 105-C03:1989	污染-Srain 褪色-Fading	Grade 4
	GB/T3921.3-1997	污染-Srain 褪色-Fading	等级 4
干湿摩擦色牢度 (CFTR.)	AATCC8:2002	干-Dry 湿-Wet	Grade 4
	GB/T3920-1997	干-Dry 湿-Wet	等级 4
抗摩擦坚牢度 (Ab.Re)	ASTM D4966-98 Martindale 12Kpa		rubs 50000转

colour 12

材质(Comp):52%涤纶(PET)+48%尼龙(N)

克重(Weight):310gsm

幅宽(Width):140cm

备注:我司面料未含阻燃,阻燃需外加工.



Company Information

Contact

(Phone)	0757-23870666 23636258
(Fax)	0757-23875234 23873536
(E-mail)	xiaowensu@hoaubrother.com
(Web)	www.hoaubrother.com
(Add)	顺德·龙江 精美路18号世博汇A座4楼(华宇总部) 亚洲国际A区一排29-32号(华宇旗舰店) No. 29-32, A area, Asia international materials city, Long Jiang, Shunde, Foshan, Guangdong, China, Post Code 528318

— HOAU BROTHER —



扫描二维码, 关注华宇兄弟

• 产品数据为真实检测数据 •