

HY2041-05



技术检测 (Tec.)	检测标准 (TS.)	项目 (Unit.)	测试结果 (Test Result)
耐水色牢度 (CFTW.)	AATCC107:2002 GB/T5713-1997	污染-Srain 褪色-Fading 污染-Srain 褪色-Fading	Grade 等级 3-3.5 3-3.5
耐汗色牢度 (CFTP.)	AATCC15:2002 GB/T3922-1997	污染-Srain 褪色-Fading 污染-Srain 褪色-Fading	Grade 等级 3-3.5 3-3.5
耐洗色牢度 (CFTW.)	ISO 105-C03:1989 GB/T3921.3-1997	污染-Srain 褪色-Fading 污染-Srain 褪色-Fading	Grade 等级 3-3.5 3-3.5
干湿摩擦色牢度 (CFTR.)	AATCC8:2002 GB/T3920-1997	干-Dry 湿-Wet 干-Dry 湿-Wet	Grade 等级 3.5-4 3.5-4
抗摩擦坚牢度 (Ab.Re)	ASTM D4966-98 Martindale 12Kpa		rubs 50000转

备注:我司面料未含阻燃,阻燃需外加工.

Company Information

Contact


(Phone)	0757-23870666 23636258
(Fax)	0757-23875234 23873536
(E-mail)	xiaowensu@hoaubrother.com
(Web)	www.hoaubrother.com
(Add)	顺德·龙江 精美路18号世博汇A座4楼(华宇总部) 亚洲国际A区一排29-32号(华宇旗舰店)

— HOAU BROTHER —




扫描二维码, 关注华宇兄弟

• 产品数据为真实检测数据 •



适用范围:办公网椅背



HY2041-05

colour 20


材质:100%涤纶

克重:400g/m²


幅宽:150cm

耐磨:50000转


色牢:4级




HY2041-18




HY2041-17




HY2041-16




HY2041-20




HY2041-12




HY2041-13




HY2041-14




HY2041-19




HY2041-11




HY2041-15




HY2041-06




HY2041-10




HY2041-09




HY2041-08




HY2041-05




HY2041-07




HY2041-01



HY2041-02



HY2041-03



HY2041-04

诚信·专业·服务

● 由于拍照光线影响及显示设备的差异,导致图片与实物存在色差,请以实物为准。